

CHEF COLLECTION



IDEAL FOR

- Professionals from the HoReCa industry.
- Multifunctional use that can be worn in different ways for higher comfort.
- Recommended as a key element in the uniform to preserve all the health quality standards.

KEY FEATURES



4-WAY
ULTRA STRETCH



95% RECYCLED
POLYESTER

REPREVE



SEAMLESS



MULTIFUNCTIONAL



ULTRALIGHT



MOISTURE
MANAGEMENT



QUICK
DRY



POLYGIENE
(antibacterial growth)



COOLING
EFFECT

HEIQ
SMART TEMP

DIMENSIONS



FABRICS COMPOSITION

95% Recycled Polyester.
5% Elastane.

COOLNET®

PACKAGING



WASHING MAINTENANCE SYMBOLS



COOLNET

Mass per unit area: EN 12127:1997	154 g/m ²	± 5 %
---	----------------------	-------

Air Permeability EN ISO 9237:1995	507,31 mm/s	± 10 %
---	-------------	--------

Thermal Resistance (RCT): EN ISO 11092:2014	0,0205 m ² K/W	± 10 %
---	---------------------------	--------

Water Vapour Resistance (RET): EN ISO 11092:2014	2,28 m ² Pa/W	± 10 %
--	--------------------------	--------

Determination of breaking Strength and elongation:

EN ISO 13934-1:2013

AVERAGE LOAD		AVERAGE ELONGATION	
LENGTHWISE	290 N ± 10 %	LENGTHWISE	195% ± 10 %
CROSSWISE	170 N ± 10 %	CROSSWISE	395% ± 10 %

Bursting resistance (after 5 washes): EN ISO 13938-1:1999	131 kPa	± 10 %
---	---------	--------

Determination of dimensional change in domestic washing and drying:

EN ISO 5077:2008

LENGTHWISE < ±3%

CROSSWISE < ±3%

Washing procedure 4N (Ta=40 ±3°C) according to ISO 6330:2012

Resistance to pilling: ISO 12945-2:2001	2 - 3	2000 CYCLES
---	-------	-------------

Scale from 1 to 5 in which 1 is "Very severe pilling" and 5 is "No pilling".

Determination of the abrasion resistance of fabrics:

EN ISO 12947-2:2016

Testing pressure: 9 kPa

>100000 CYCLES
Until the first yarn broken**Fastness rates:**

Colour fastness to domestic and commercial laundering:

EN ISO 105-C06:2010

3 - 4 *

Colour fastness to perspiration (Alkaline & Acid):

EN ISO 105-E04:2013

ALKALINE

4 - 5 *

ACID

4 - 5 *

Colour fastness to rubbing (Dry & Wet):

EN ISO 105-X12:2016

DRY

4 - 5 *

WET

4 - 5 *

Colour fastness to sea water:

EN ISO 105-E02:2013

4 - 5 *

Colour fastness to artificial light:

EN ISO 105-B02:2014 Método 2

4**

* Fastness rates in a scale from 1 to 5 in which 1 is "Poor behaviour" and 5 is "Good behaviour".

** Fastness to artificial light rates in a scale from 1 to 8 in which 1 is "Very poor" and 8 is "Excellent"