

# GUANTE NITRILO GRIPPAZ® BY JUBA® - 580NR GRIPPAZ

"GRIPPAZ" Guante desechable de nitrilo ambidiestro, escamado, sin polvo.



## NORMATIVA



## ESPECIALES

### GUANTES DE TRABAJO RECOMENDADOS PARA:

- Galvanizados
- Montajes ligeros
- Mantenimiento de vehículos
- Agricultura y horticultura
- Limpieza y mantenimiento industrial
- Industria alimentaria
- Procesado de alimentos
- Tatuadores (580NR)
- Peluquerías

### CARACTERÍSTICAS

- Diseño en escamas patentado a nivel mundial que permite que exista mayor superficie de contacto por lo que ofrece un mayor agarre en condiciones mojadas y aceitadas, superior al acabado en diamante.
- Zona texturizada en el interior del pulgar que ofrece un mejor agarre.
- Más grueso que un guante desechable tradicional por lo que proporciona mayor resistencia a la elongación y al desgarrado, convirtiéndose en un guante muy duradero.
- El nitrilo aporta mayor durabilidad,

elasticidad y resistencia a la perforación, además se adapta térmicamente a la mano para un ajuste perfecto.

- **Ambidextros.**
- **Texturizado en su exterior para maximizar el agarre y texturizado interior que evita el desplazamiento por sudoración.**
- **Adecuados para personas alérgicas al látex.**
- **Apto para uso alimentario.**
- **Para protección antiviral, el guante supera la norma ISO 16604, método de prueba B. (EN ISO 374-5: VIRUS).**
- **Este guante protege contra las siguientes sustancias químicas: n-Heptano (nivel 3, >60 minutos), Hidróxido Sódico 40% (nivel 6, >480 minutos), Peróxido de hidrógeno 30% (nivel 3, >60 minutos) y Formaldehído 37% (nivel 5, >240 minutos).**
- **Disponible en bolsas de 10 unidades (Ref. B580OR).**

#### MÁS INFORMACIÓN

<b>Materiales</b>	<b>Grueso</b>	<b>Largo</b>	<b>Tallas</b>	<b>Embalaje</b>
Nitrilo	0.15 mm	S - 24 cm M - 24 cm L - 24 cm XL - 24 cm XXL - 24 cm	7/S 8/M 9/L 10/XL 11/XXL	Cajita:50und/Caja:500und

NORMATIVAS

ENISO374-1:2016



**EN ISO 374-1:2016**  
**TIPO X**



**XXXXXX**

**EN ISO 374-5:2016**



The EN374: 2003 standard is renamed ENISO374: 2016. The purpose of this standard is to classify gloves according to their behavior when exposed to chemical substances.

They are divided into the following parts:

**EN ISO 374-1:2016** - Terminology and performance requirements for chemical risks.

**EN 374-2:2014** - Determination of resistance to penetration.

**EN 16523-1:2015 + A1:2018** - Permeation by liquid chemicals under continuous contact conditions.

**EN ISO 374-4:2019** - Determination of resistance to chemical degradation.

**EN ISO 374-5:2016** - Terminology and requirements demanded for risks of microorganisms.

**Gloves classification according to ENISO374-1: 2016**

Gloves are divided into three types:

**EN ISO 374-1:2016**  
**TIPO A**



**UVWXYZ**

**TYPE A**

Step time ≥ 30 min for at least 6 products

**EN ISO 374-1:2016**  
**TIPO B**



**XYZ**

**TYPE B**

Step time ≥ 30 min for at least 3 products

**EN ISO 374-1:2016**  
**TIPO C**



**TYPE C**

Step time ≥ 10 min for at least 1 products

the advancement of chemicals at the molecular level. The resistance of the glove material to permeation by a chemical is determined by measuring the time it passes through the material.

**Modification of the ENISO374-5: 2016 standard**

When the glove passes the test described for virus protection, the word "virus" will appear under the pictogram. If nothing appeared, protection would only be assured against bacteria.

Letter	Chemical substance	Cas number	Class
A	Methanol	67-56-1	Primary alcohol
B	Acetone	67-64-1	Cetone
C	Acetonitrile	75-05-8	Nitrile compound
D	Dichloromethane	75-09-2	Chlorine hydrocarbon
E	Carbon disulfide	75-15-0	Sulphate organic compound
F	Toluene	108-88-3	Aromatic hydrocarbon
G	Diethylamine	109-89-7	Amine
H	Tetrahydrofuran	109-99-9	Heterocyclic ether
I	Ethyl acetate	141-78-6	Ester
J	N-heptane	142-85-5	Saturated hydrocarbon
K	Sodium hydroxide 40%	1310-73-2	Inorganic alkaline
L	Sulphuric acid 96%	7664-93-9	Inorganic, oxidising mineral acid
M	Nitric acid 65%	7697-37-2	Inorganic, oxidising mineral acid
N	Acetic acid 99%	64-19-7	Organic acid
O	Ammonia hydroxide 25%	1332-21-6	Organic alkaline
P	Hydrogen peroxide 30%	7722-84-1	Peroxide
S	Hydrofluoric acid 40%	7664-39-3	Mineral organic acid
T	Formaldehyde 37%	50-00-0	Aldehyde

**Levels of resistance to permeability**

Taverage penetration time	Performance levels	Average penetration time	Performance levels
> 10	Class 1	> 120	Class 4
> 30	Class 2	> 240	Class 5
> 60	Class 3	> 480	Class 6

**Gloves classification according to EN374-2:2014**

It is the advance of chemical products through the material, seams of the glove at a non-molecular level. Air leak test: the glove is inflated with air and immersed in water. The appearance of air bubbles is controlled within 30 '. Water leak test: the glove is filled with water and the appearance of water droplets is controlled. If these tests are positive, the pictogram will be put on.

**Gloves classification according to EN374-4: 2013**

Detriment to some of the glove's properties due to contact with a chemical. Eg: discoloration, hardening, softening, etc. Permeation test EN 16523-1. It is